

# SS Slick'em



## Technical Data Sheet MICRO-TOPPING MIX

### PRODUCT DESCRIPTION

SS Slick'em is trowel-grade micro-topping of Portland cement, fine aggregates and proprietary admixes. SS Slick'em may be applied to properly prepared and sound interior substrates creating a new canvas that may be stained, sanded and scored.

### BENEFITS AND FEATURES

- Create a new canvas, perfect for staining and or scoring.
- Micro-topping that provides depth.
- Beautiful slick surface for interior floors.
- Easy to use, just add water.-

### TECHNICAL INFORMATION

|                             |                       |
|-----------------------------|-----------------------|
| Finish .....                | Must be topped coated |
| Drying time(re-coat) .....  | 4 hours at 72°F       |
| Drying time(staining) ..... | Overnight             |
| Clean up.....               | Warm, soapy water     |

*Please note that low air and/or concrete temperatures and/or relative humidity may extend drying times. Follow recommended coverage rates for best results.*

### APPROXIMATE COVERAGE RATES

400 - 700 sq. ft. per gallon  
2000 - 3500 sq. ft. per 5 gallons  
Depending on surface profile.

### SURFACE PREPARATION

We recommend preparation of the substrate be performed in accordance with ICRI Guideline No 03732, minimum concrete surface profile(CSP) of 1. This will insure that the surface is clean, dry and free of grease, oil, and sealers and open to receive SS Slick'em.

### BOND COAT

Before applying SS Slick'em, dampen the substrate with a solution of 3 parts water to 1 part SS Liquid Polymer (3:1).

### COLORING

SS Slick'em may be colored integrally with enCOLOR or with SS Sedona Acid Stain, SS Rainbow System, or SS DYE-namic Acetone Dye. If acid staining the surface, it is recommended to create a sample surface on which to test different dilution rates. A rule of thumb may be to start with 10 parts water to 1 part acid stain.

### MIXING

Start by dry mixing contents first. Add 5 gallons of SS Slick'em to a solution of 1.5 to 2 gallons of clean water. Mix well until the SS Slick'em is a creamy consistency.

### APPLICATION

Pour the mixed SS Slick'em onto the dampened substrate in a long thin line. Spread with a metal squeegee, hand trowel, or magic trowel. Apply as thin as possible while maintaining a wet edge. Allow the first coat to thoroughly dry before applying the second coat. Two applications are recommended. SS Slick'em is not a heavy build product. Do necessary patching prior to applying.

### CLEAN UP

Use water and a scrub brush. Dispose of containers in accordance with local and federal regulations.

### PRODUCT REMOVAL

SS Slick'em needs to be mechanically ground to be removed.

### SHELF LIFE

SS Slick'em has a shelf Life of one year in its original, sealed, unopened bag.

### PACKAGING

SS Slick'em comes in white or grey in 50# bags.

### PRECAUTIONS AND LIMITATIONS

- Application on surfaces with loose, deteriorated concrete or with coating that may subsequently loosen are not suitable hosts for micro-topping products.
- Coverage rates depend upon many conditions including application method, surface porosity, applicator, ambient conditions, etc.
- SS Slick'em is not a heavy build product and an interior use product only. Do all necessary patching and filling prior to applying.
- It is recommended to test this product prior to using on entire application.
- Keep away from children.

### SPECIAL NOTES

Please consult Safety Data Sheet (SDS) and read Warranty information prior to use. This information can be requested by contacting customer service at 866-906-2006.

### WARRANTY

SS Specialties and its affiliates warrant our products to be of good quality, free of defects and will conform to our published specification in force on the date of acceptance of the order. As the exclusive remedy for breach of this warranty, SS Specialties will replace defective materials ninety days after SS Specialties has shipped the product. All our warranty and other duties with respect to the quality of materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates, and no action for breach of any said duties may thereafter be commenced. No warranty is expressed or implied as to the length of life of this product or merchantability or fitness. Liability, if any, is limited to the purchase price of the material. Under no circumstances will SS Specialties be liable for any consequential damages in excess of the purchase price of the product.



[www.ssspecialtiesconcrete.com](http://www.ssspecialtiesconcrete.com)

Distributed by SS Specialties | 121 NE 40th Street | Oklahoma City, OK 73105 USA | Phone 866-906-2006 | Fax 405-525-3367

SSSlick'em July 2017  
07/19/2017